



## Waxing Iron Temperatures

### Waxing Iron Temperatures

Temps are a guideline as each iron may vary slightly.

Test the wax on the iron before applying the iron to the ski

| Wax  | Setting Low   | Setting High  |  |
|--|---|---|--|
| Base Prep<br>HS 40 Yellow<br>HSLF 40 Yellow<br>HSF 40 Bronze | Digital Iron 250 F<br>Standard Dial Iron<br>5 to 6 Medium   | Digital Iron 265 F<br>Standard Dial Iron<br>5 to 6 Medium   |  |
| HS 30 Red<br>HSLF 30 Red<br>HSF 30 Salmon                    | Digital Iron 260 F<br>Standard Dial Iron<br>6 to 7 Medium   | Digital Iron 275 F<br>Standard Dial Iron<br>6 to 7 Medium   |  |
| HS 20 Blue<br>HSLF 20 Blue<br>HSF 20 Tan                     | Digital Iron 265 F<br>Standard Dial Iron<br>6 to 8 Medium   | Digital Iron 280 F<br>Standard Dial Iron<br>6 to 8 Medium   |  |
| HS 10 Teal<br>HSLF 10 Teal<br>HSF 10 Green<br>HS - 0 White   | Digital Iron 275 F<br>Standard Dial Iron<br>7 to 8.5 Medium | Digital Iron 285 F<br>Standard Dial Iron<br>7 to 8.5 Medium |  |